




PRODUCT DATA SHEET

TWO SIDE TREATED, NON-SEALABLE, TRANSPARENT BOPP FILM

IMP112



Non-heat seal corona treated layer
High transparency OPP Core
Non-heat seal corona treated layer

Non-sealable, two side corona treated BOPP film. IMP112 is designed for use in laminate structures as the surface web.

PRODUCT FEATURES

- Excellent ink adhesion on the treated surfaces
- Outstanding clarity and gloss
- Good antistatic and slip properties
- Food contact suitable

APPLICATIONS

- Suitable for reverse print and lamination applications
- Suitable for overlamination of labels
- Suitable for lamination to a wide range of polymer and non-polymer flexible materials
- Suitable for use in HFFS and VFFS applications with fin seals
- Compatible with most print, ink and adhesive systems.

PROPERTIES	TEST METHOD	UNITS	IMP112	IMP112	IMP112	IMP112	IMP112	IMP112	IMP112	
GENERAL										
Thickness	Internal	ga	47	58	71	80	100	118	157	
Yield	ASTM D-1505	lb/ream	6.7	8.4	10.1	11.2	14.0	16.8	22.4	
	Internal	in ² /lb	64400	51500	42900	38600	30900	25700	19300	
OPTICAL										
Haze	ASTM D-1003	%					≤ 1.2			
Gloss	ASTM D-2457	@60°C					> 90			
SURFACE										
Wetting Tension	ASTM D-2578	dynes/cm					≥ 38*			
COF	Both sides	ASTM D-1894	Film-Film		≤ 0.50					
MECHANICAL										
Tensile Strength (at break)	MD	ASTM D-882	psi		> 17300					
	TD	ASTM D-882	psi		> 14400					
Elongation to Break	MD	ASTM D-882	%		< 180					
	TD	ASTM D-882	%		< 70					
THERMAL										
Shrinkage (250°F/2 min)	MD	Internal	%		≤ 4.0					
	TD	Internal	%		≤ 2.0					
BARRIER										
Water Vapour Transmission Rate	(100°F/90% RH)	ASTM F1249	g/100in ² /24h	0.68	0.61	0.55	0.48	0.39	0.32	0.26

* for up to 12 months from manufacture

Guidelines for storage

Temperature should be less than 86°F and humidity 55±5% in storage areas and material should be consumed within 6 months of receipt. Allow film to reach operating room temperature 24h before use.

FDA Compliance: For information regarding food contact compliance, please contact your Impak Films representative

Information in this publication refers to average values of laboratory tests on samples from standard production. It is believed to be accurate and is given in good faith, but it is for the customer to satisfy the suitability for its own particular purpose. Accordingly, Impak Films gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. This document is not a product specification. Impak Films reserves the right to change the data sheet at any time without prior notification.

IMPAK FILMS AUSTRALIA (www.impakfilms.com.au)
 ABN: 42 586 823 597 Address: Unit 1, 15-21 Butler Way, (P.O. Box 1114), Tullamarine Vic. 3043, Australia Telephone: +61 3 9310 5540 Facsimile: +61 3 9310 5590

IMPAK FILMS USA (www.impakfilms.com)
 Address: Suite 1650, Building One, 2727 Paces Ferry Road, Atlanta, Georgia 30339, USA Telephone: +1 678 384 5520 Facsimile: +1 678 384 5543