




PRODUCT DATA SHEET

STANDARD BARRIER, ONE SIDE SEALABLE, METALLIZED BOPP

IMP120



Metallized surface layer
OPP Core
Heat seal layer

Standard barrier, metallized BOPP film suitable for surface print or lamination applications. The non-metallized side is heat sealable and suitable for cold seal application. IMP120 is designed for use in laminate and single web structures.

PRODUCT FEATURES

- Standard barrier to moisture and oxygen
- Excellent metal adhesion
- High seal strength
- Food contact suitable

APPLICATIONS

- Suitable for print and lamination applications
- Suitable for heat seal or cold seal applications
- Suitable for HFFS, VFFS and bag or pouchmaking applications
- Compatible with most print, ink and adhesive systems.
- Suitable for products requiring standard barrier or decorative metallisation

PROPERTIES	TEST METHOD	UNITS	IMP120	IMP120	IMP120	IMP120	IMP120		
GENERAL									
Thickness	Internal	ga	58	71	100	110	118		
Yield	ASTM D-1505	lb/ream	8.4	10.1	14.0	15.7	16.8		
	Internal	in ² /lb	51500	42900	30900	27600	25700		
SURFACE									
Wetting Tension	ASTM D-2578	dynes/cm						≥ 38*	
COF	Seal side	ASTM D-1894	Film-Film						≤ 0.50
MECHANICAL									
Tensile Strength (at break)	MD	ASTM D-882	psi						> 17300
	TD	ASTM D-882	psi						> 14400
Elongation to Break	MD	ASTM D-882	%						< 180
	TD	ASTM D-882	%						< 70
THERMAL									
Heat seal range		QB/T2358	*F						240 - 290
Seal Strength			g/inch						500
Shrinkage (250°F/2 min)	MD	Internal	%						≤ 4.0
	TD	Internal	%						≤ 2.0
BARRIER									
Water Vapour Transmission Rate	(100°F/90% RH)	ASTM F1249	g/100in ² /24h						< 0.05
Oxygen Transmission Rate	(73°F/0% RH)	ASTM D3985	cc/m ² /24h						< 6.5

* for up to 6 months from manufacture

Guidelines for storage

Temperature should be less than 86°F and humidity 55±5% in storage areas and material should be consumed within 6 months of manufacture. Allow film to reach operating room temperature 24h before use.

Guidelines for printing

IMP120 is suitable for printing directly onto the metal surface of the film however best results are obtained by using a suitable primer before printing. Your ink consultant should be contacted for advice on printing this material.

FDA Compliance: For information regarding food contact compliance, please contact your Impak Films representative

Information in this publication refers to average values of laboratory tests on samples from standard production. It is believed to be accurate and is given in good faith, but it is for the customer to satisfy the suitability for its own particular purpose. Accordingly, Impak Films gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. This document is not a product specification. Impak Films reserves the right to change the data sheet at any time without prior notification.

IMPAK FILMS AUSTRALIA (www.impakfilms.com.au)
 ABN: 42 586 823 597 Address: Unit 1, 15-21 Butler Way, (P.O. Box 1114), Tullamarine Vic. 3043, Australia Telephone: +61 3 9310 5540 Facsimile: +61 3 9310 5590

IMPAK FILMS USA (www.impakfilms.com)
 Address: Suite 1650, Building One, 2727 Paces Ferry Road, Atlanta, Georgia 30339, USA Telephone: +1 678 384 5520 Facsimile: +1 678 384 5543