




TECHNICAL DATA SHEET

TWO SIDE TREATED METALLIZED PET FILM

IMP226



Vacuum applied aluminum layer  
Metal adhesion copolymer layer  
Transparent polyester core  
Corona treated non-sealing polyester side

IMP226 is a biaxially oriented polyester film with metal on copolymer side. It has good oxygen and moisture barrier properties and is suitable for use in a wide variety of printed and laminated packaging applications.

PRODUCT FEATURES

- Suitable for printing and lamination on the metallized side
- Designed to give good metal bond strength to copolymer layer
- Suitable for dry laminations to other flexible materials
- Excellent gloss and optical density

APPLICATIONS

- Printed, laminated rewinds, pouches, sachets and bags
- Applications in fresh and dried foods
- Snack foods and other flexible laminates

PROPERTIES	TEST METHOD	UNITS	IMP226
<b>GENERAL</b>			
Thickness*	Internal	ga	48
Density	Internal	g/cm <sup>3</sup>	1.40
Yield	Internal	lb/ream	10.3
	Internal	in <sup>2</sup> /lb	41850
Treatment	Metal side	ASTM D-2578	60
<b>OPTICAL</b>			
Optical Density	Internal		>3.0
<b>MECHANICAL</b>			
Tensile Strength	MD	ASTM D-882	psi
	TD	ASTM D-882	psi
Elongation to Break	MD	ASTM D-882	%
	TD	ASTM D-882	%
Shrinkage 300°F / 30 min	MD	ASTM D-1204	%
	TD	ASTM D1204	%
Metal Bond Strength		Internal	gf/in
Coefficient of Friction	Static	ASTM D-1894	0.60
	Dynamic	ASTM D-1894	0.55
<b>BARRIER</b>			
Water Vapor Transmission Rate	(100°F/90% RH)	ASTM E96	g/100in <sup>2</sup> /24h
Oxygen Transmission Rate	(73°F/0% RH)	ASTM D3985	cc/100in <sup>2</sup> /24h

\* Thicker materials may be available on request

Guidelines for storage

IMP226 should be stored at below 105°F in its original wrapping and away from sources of direct sunlight.

Printing & Lamination

Consult with your ink and adhesive suppliers for appropriate materials for use with this product.

FDA Compliance: For information regarding food contact compliance, please contact your Impak Films representative

Information in this publication refers to average values of laboratory tests on samples from standard production. It is believed to be accurate and is given in good faith, but it is for the customer to satisfy the suitability for its own particular purpose. Accordingly, Impak Films gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. This document is not a product specification. Impak Films reserves the right to change the data sheet at any time without prior notification.

IMPAK FILMS AUSTRALIA (www.impakfilms.com.au)  
ABN: 42 586 823 597 Address: Unit 1, 15-21 Butler Way, (P.O. Box 1114), Tullamarine Vic. 3043, Australia Telephone: +61 3 9310 5540 Facsimile: +61 3 9310 5590

IMPAK FILMS USA (www.impakfilms.com)  
Address: 2727 Paces Ferry Road, Suite 1650 Building One, Atlanta, Georgia 30339, USA Telephone: +1 678 384 5520 Facsimile: +1 678 384 5543