




**TRANSPARENT, VERY HIGH BARRIER PET FILM FOR
RETORT APPLICATIONS**

IMP243



AIOx top coated, very high barrier polyester surface
Transparent polyester core

IMP243 is a transparent AIOx PET film which has been top coated to give very high oxygen and moisture barrier properties. IMP243 is suitable for printing and lamination and is designed for use in a variety of flexible packaging applications including retort and hot water sterilization.

PRODUCT FEATURES

- Very high oxygen and moisture barrier
- Excellent gloss and transparency
- Can be printed and laminated on the top coated side
- Suitable for use in retort and hot water sterilization applications

APPLICATIONS

- Very high barrier products that are not light sensitive
- Suitable for meat, fish, nuts, dried fruit, cheese and dried meats
- Used in a laminate structure to provide very high barrier flexible material suitable for form fill and seal, pouch, bag and lidding applications.
- Used in laminate structures to provide very high barrier materials for steam and hot water sterilization processes

| PROPERTIES | TEST METHOD | UNITS | IMP243 | |
|-------------------------------|----------------|---------------------|----------------------------|-------|
| GENERAL | | | | |
| Thickness | Internal | ga | 48 | |
| Density | Internal | g/cm ³ | 1.40 | |
| Yield | Internal | lb/ream | 10.3 | |
| | Internal | in ² /lb | 41800 | |
| Surface Tension | Coated | ASTM D-2578 | dynes/cm | 40 |
| OPTICAL | | | | |
| Haze | max | ASTM D-1003 | % | 3.0 |
| MECHANICAL | | | | |
| Tensile Strength | MD | ASTM D-882 | psi | 28800 |
| | TD | ASTM D-882 | psi | 31300 |
| Elongation to Break | MD | ASTM D-882 | % | 100 |
| | TD | ASTM D-882 | % | 100 |
| Shrinkage 300°F / 30 min | MD | ASTM D-1204 | % | 2.0 |
| | TD | ASTM D1204 | % | 0.4 |
| Coefficient of Friction | Static | ASTM D-1894 | | 0.60 |
| | Dynamic | ASTM D-1894 | | 0.55 |
| BARRIER | | | | |
| Water Vapor Transmission Rate | (100°F/90% RH) | ASTM E96 | g/100in ² /24h | 0.06 |
| Oxygen Transmission Rate | (73°F/0% RH) | ASTM D3985 | cc/100in ² /24h | 0.09 |

Guidelines for storage

IMP243 should be stored at below 105°F in its original wrapping and away from sources of direct sunlight.

Printing & Lamination

Consult with your ink and adhesive suppliers for appropriate materials for use with this product.

FDA Compliance: For information regarding food contact compliance, please contact your Impak Films representative

Information in this publication refers to average values of laboratory tests on samples from standard production. It is believed to be accurate and is given in good faith, but it is for the customer to satisfy the suitability for its own particular purpose. Accordingly, Impak Films gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. This document is not a product specification. Impak Films reserves the right to change the data sheet at any time without prior notification.

IMPAK FILMS AUSTRALIA (www.impakfilms.com.au)
 ABN: 42 586 823 597 Address: Unit 1, 15-21 Butler Way, (P.O. Box 1114), Tullamarine Vic. 3043, Australia Telephone: +61 3 9310 5540 Facsimile: +61 3 9310 5590

IMPAK FILMS USA (www.impakfilms.com)
 Address: 2727 Paces Ferry Road, Suite 1650 Building One, Atlanta, Georgia 30339, USA Telephone: +1 678 384 5520 Facsimile: +1 678 384 5543