




**TECHNICAL DATA SHEET**

**ONE SIDE PVdC COATED MATTE BOPP**

**IMP674**



A PVdC coated transparent matte BOPP film with good oxygen, aroma and flavor barrier. IMP674 offers superior mechanical properties and flex crack resistance in laminates. The use of IMP674 in laminate materials can assist in the extension of shelf life in a range of oxygen sensitive food products.

**PRODUCT FEATURES**

- Excellent oxygen barrier
- Excellent flavor and aroma barrier
- Superior flex crack resistance
- Superior matte and contact transparency
- Excellent printability on the PVdC coated side

**APPLICATIONS**

- Used in laminates to achieve high gas barrier properties
- Barrier layer in laminates for cheese, meat, nuts, cereals, flavored, powdered and processed foods
- Barrier layer for overwrap applications such as cosmetics and personal care products

PROPERTIES	TEST METHOD	UNITS	IMP674
<b>GENERAL</b>			
Base Web Thickness	GB/T6672	ga	83
Yield	Q/SN2	lb/ream	10.5
		in <sup>2</sup> /lb	40900
Treatment Level	PVdC side GB/T14216	dyne/cm	52
Haze	Maximum GB2410	%	73.0
Coefficient of Friction (CoF)	PVdC-PVdC GB10006	Kinetic	0.45
<b>MECHANICAL</b>			
Tensile Strength	MD GB/T13022	psi	16700
	TD GB/T13022	psi	33500
Elongation to Break	MD GB/T13022	%	220
	TD GB/T13022	%	65
Shrinkage (250°F / 2min)	MD Q/SN2	%	1.60
	TD Q/SN2	%	0.65
<b>BARRIER</b>			
Water Vapor Transmission Rate	100°F/90% RH ISO 15106-3	g/100in <sup>2</sup> /24h	0.44
Oxygen Transmission Rate	73°F/0% RH ASTM D3985	cc/100in <sup>2</sup> /24h	0.91

**Guidelines for storage**

Temperature should be less than 86°F and humidity 55±5% in storage areas. Material should be consumed within 6 months of receipt. Allow film to reach operating room temperature 24h before use.

**Printing & Lamination**

It is recommended to print on the PVdC coated side of the film when used in a laminate structure. Advice should be taken from your ink supplier. When laminating this material, the use of a lamination film free from migratory additives may give improved results.

*FDA Compliance: For information regarding food contact compliance, please contact your Impak Films representative*

Information in this publication refers to average values of reference data and/or laboratory tests on samples from standard production. It is believed to be accurate and is given in good faith, but it is for the customer to determine the suitability of the material for its own particular purpose or application. Accordingly, Impak Films USA LLC gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. This document is not a product specification. Impak Films reserves the right to amend this product data sheet at any time without prior notification.

IMPAK FILMS AUSTRALIA (www.impakfilms.com.au)  
 ABN: 42 586 823 597 Address: Unit 1, 15-21 Butler Way, (P.O. Box 1114), Tullamarine Vic. 3043, Australia Telephone: +61 3 9310 5540 Facsimile: +61 3 9310 5590

IMPAK FILMS USA (www.impakfilms.com)  
 Address: 2727 Paces Ferry Road, Suite 1650 Building One, Atlanta, Georgia 30339, USA Telephone: +1 678 384 5520 Facsimile: +1 678 384 5543