




**TECHNICAL DATA SHEET**

**NON-SEALABLE MATTE BOPP**

**IMP180**



Non sealable matte surface layer  
OPP Core  
Non-sealable layer

Matte surfaced BOPP with high contact transparency and a smooth matte appearance. IMP180 is designed to prevent light reflectivity and improve the visual appearance of products and materials in high light situations.

**PRODUCT FEATURES**

- Smooth, matte surface
- Excellent contact clarity
- Excellent print receptivity and lamination bonds
- Food contact suitable
- Good antistatic properties
- Available one or both sides corona treated

**APPLICATIONS**

- Suitable for print and lamination applications
- Suitable as a top web in label laminates
- Suitable for packaging applications when laminated to a sealant layer
- Compatible with most print, ink and adhesive systems.

PROPERTIES	TEST METHOD	UNITS	IMP180	IMP180	IMP180	IMP180	
<b>GENERAL</b>							
Thickness	Internal	ga	58	71	100	118	
Yield	ASTM D-1505	lb/ream	7.7	9.5	13.4	16.0	
	Internal	in <sup>2</sup> /lb	55800	45400	32300	26900	
<b>SURFACE</b>							
Wetting Tension	ASTM D-2578	dynes/cm	≥ 38*				
COF	Both sides	ASTM D-1894	Film-Film	≤ 0.40			
<b>MECHANICAL</b>							
Tensile Strength (at break)	MD	ASTM D-882	psi	> 17300			
	TD	ASTM D-882	psi	> 14400			
Elongation to Break	MD	ASTM D-882	%	< 180			
	TD	ASTM D-882	%	< 70			
<b>THERMAL</b>							
Heat seal range			°F	240 - 290			
Seal Strength	QB/T2358		g/inch	500			
Shrinkage (250°F/2 min)	MD	Internal	%	≤ 4.0			
	TD	Internal	%	≤ 2.0			
<b>BARRIER</b>							
Water Vapor Transmission Rate	(100°F/90% RH)	ASTM F1249	g/100in <sup>2</sup> /24h	0.57	0.48	0.39	0.32

\* for up to 6 months from manufacture

**Guidelines for storage**

Temperature should be less than 86°F and humidity 55±5% in storage areas and material should be consumed within 6 months of manufacture. Allow film to reach operating room temperature 24h before use.

*FDA Compliance: For information regarding food contact compliance, please contact your Impak Films representative*

Information in this publication refers to average values of laboratory tests on samples from standard production. It is believed to be accurate and is given in good faith, but it is for the customer to satisfy the suitability for its own particular purpose. Accordingly, Impak Films gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. This document is not a product specification  
Impak Films reserves the right to change the data sheet at any time without prior notification.

30-Jul-14