




TECHNICAL DATA SHEET

ONE SIDE CORONA TREATED MATTE PET

IMP232



Corona treated matte surface layer
Matte polyester core
Plain matte side

Matte biaxially oriented polyester film, one side corona treated, one side plain for lamination, labelling and flexible packaging applications.

PRODUCT FEATURES

- Can be printed and laminated on the corona side
- Smooth matte surface with excellent contact transparency
- Good machinability for use in HFFS and VFFS processes or as a label

APPLICATIONS

- Reverse print and lamination in rewinds, bag, pouch and label applications
- Labels and other materials requiring reduced glare and a high end satin -finish appearance

PROPERTIES	TEST METHOD	UNITS	IMP232	IMP232	IMP232
------------	-------------	-------	--------	--------	--------

GENERAL

Thickness	Internal	ga	48	92	200
Density	Internal	g/cm ³		1.40	
Yield	Internal	lb/ream	10.3	19.8	43.0
	Internal	in ² /lb	41850	21800	10050
Treatment	Corona side	ASTM D-2578		56	
	Plain side	ASTM D-2578		42	

OPTICAL

Haze	ASTM D-1003	%	47	65	83
Transmittance	ASTM D-1003		87	85	83
Gloss	ASTM D-2457	%	48	42	40

MECHANICAL

Tensile Strength	MD	ASTM D-882	psi	31300	28200	28200
	TD	ASTM D-882	psi	29000	28200	28200
Elongation to Break	MD	ASTM D-882	%	100	100	100
	TD	ASTM D-882	%	80	70	70
Film Melting Point		DSC	°F		490	
Shrinkage 300°F / 30 min	MD	ASTM D-1204	%	2.0	1.8	1.6
	TD	ASTM D1204	%	0.4	0.4	0.4
Coefficient of Friction	Static	ASTM D-1894			0.35	
	Dynamic	ASTM D-1894			0.26	

BARRIER

Water Vapor Transmission Rate	(100°F/90% RH)	ASTM E96	g/100in ² /24h	2.60	1.40	0.60
Oxygen Transmission Rate	(73°F/0% RH)	ASTM D3985	cc/100in ² /24h	6.50	4.50	2.60

Guidelines for storage

IMP232 should be stored at below 105°F in its original wrapping and away from sources of direct sunlight.

Printing & Lamination

Consult with your ink and adhesive suppliers for appropriate materials for use with this product.

FDA Compliance: For information regarding food contact compliance, please contact your Impak Films representative

Information in this publication refers to average values of laboratory tests on samples from standard production. It is believed to be accurate and is given in good faith, but it is for the customer to satisfy the suitability for its own particular purpose. Accordingly, Impak Films gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. This document is not a product specification. Impak Films reserves the right to change the data sheet at any time without prior notification.

IMPAK FILMS AUSTRALIA (www.impakfilms.com.au)
 ABN: 42 586 823 597 Address: Unit 1, 15-21 Butler Way, (P.O. Box 1114), Tullamarine Vic. 3043, Australia Telephone: +61 3 9310 5540 Facsimile: +61 3 9310 5590

IMPAK FILMS USA (www.impakfilms.com)
 Address: 2300 Lake Park Drive, Suite 270, Smyrna, Georgia 30080, USA Telephone: +1 678 384 5520 Facsimile: +1 678 384 5543