
TECHNICAL DATA SHEET

TRANSPARENT HIGH OXYGEN BARRIER POLYESTER FILM

IMP661



A transparent PET film with high oxygen barrier and transparency. IMP661 offers superior mechanical properties and flex crack resistance in laminates. IMP661 can be used as a substitute for traditional transparent barrier films like PVdC / acrylic coated films and multilayer co-extruded films in flexible packaging.

PRODUCT FEATURES

- · Excellent oxygen barrier
- · Superior flex crack resistance
- Halogen free chemical coated surface for printing and lamination
- · Excellent surface gloss and high transparency
- · Not suitable for retort applications

APPLICATIONS

- Substitute for PVdC / Acrylic coated flexible films
- · Substitute for multilayer co-extruded barrier films
- Barrier layer in laminates for cheese, meat, nuts, cereals, flavored powdered and processed
- Barrier layer for overwrap applications such as cosmetics and personal care products

		1		
PROPERTIES		TEST METHOD	UNITS	IMP661
GENERAL				
Base Web Thickness		Internal	ga	48
Yield		ASTM D1505	lb/ream	10.3
rielu		Internal	in²/lb	41800
Treatment Level	Chemical side	- ASTM D-2578	dyne/cm	56
	Plain side			42
Haze		ASTM D-1003	%	3.5
Coefficient of Friction (CoF)	A-B	- ASTM D-1894 ·	Static	0.80
	A-B		Kinetic	0.65
MECHANICAL				
Tensile Strength (minimum at break)	MD	ASTM D-882	psi	30000
	TD	ASTM D-882	psi	30000
Elongation to Break (minimum at break)	MD	ASTM D-882	%	100
	TD	ASTM D-882	%	90
THERMAL				
Max. Shrinkage (300°F/30 min)	MD	ASTM D-1204	%	2.5
	TD	ASTM D-1204	%	0.4
BARRIER				
Oxygen Transmission Rate	(73°F/0% RH)	ASTM D3985	cc/100in²/24h	< 0.26

Guidelines for storage

Temperature should be less than 86°F and humidity 55±5% in storage areas. Material should be consumed within 6 months of receipt. Allow film to reach operating room temperature 24h before use.

Printing & Lamination

It is recommended to print on the chemically coated side of the film when used in a laminate structure. Vinyl ester based and NC/PU based inks offer good adhesion performance but advice should be taken from your ink supplier.

When laminating this material, the use of a lamination film free from migratory additives may give improved results.

FDA Compliance: For information regarding food contact compliance, please contact your Impak Films representative

Information in this publication refers to average values of reference data and/or laboratory tests on samples from standard production. It is believed to be accurate and is given in good faith, but it is for the customer to determine the suitability of the material for its own particular purpose or application. Accordingly, Impak Films USA LLC gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. This document is not a product specification. Impak Films reserves the right to amend this product data sheet at any time without prior notification.

IMPAK FILMS AUSTRALIA (www.impakfilms.com.au)
ABN: 42 586 823 597 Address: Unit 1, 15-21 Butler Way, (P.O. Box 1114), Tullamarine Vic. 3043, Australia Te