




TECHNICAL DATA SHEET

ONE SIDE BARRIER PVdC COATED, ONE SIDE ACRYLIC COATED BOPP

IMP675



Acrylic coated print /seal surface
BOPP Base film
Barrier PVdC coated sealable surface

One side PVdC coated for high oxygen barrier and sealability, one side Acrylic coated for printing or sealing. IMP675 offers low and stable COF on the acrylic side for high performance machinability in a single web or in laminations.

PRODUCT FEATURES

- Excellent oxygen and moisture barrier
- Excellent flavor and aroma barrier
- Excellent printability on the Acrylic coated side
- Sealable either side and lap sealable
- High clarity and gloss

APPLICATIONS

- Used as a single layer this film may be suitable for packaging baked goods, desserts, snacks and other oxygen sensitive products
- Used in a lamination this film may be suitable for packaging of spices, powders, dried coffee and other products sensitive to oxygen, moisture and loss of flavor/aroma

PROPERTIES	TEST METHOD	UNITS	IMP675	IMP675	IMP675
GENERAL					
Base Web Thickness	GB/T6672	ga	83	100	122
Yield	Q/SN2	lb/ream	13.5	15.7	19.0
		in ² /lb	32000	27500	22700
Treatment Level	Acrylic side	GB/T14216	dyne/cm	42	42
Haze	Maximum	GB2410	%	4.8	4.8
Gloss (45°)	Acrylic side	GB/T8807	%	100	100
Coefficient of Friction (CoF)	PVdC-PVdC	GB10006	Kinetic	0.25	0.25
MECHANICAL					
Tensile Strength	MD	GB/T13022	psi	18900	18900
	TD	GB/T13022	psi	36300	36300
Elongation to Break	MD	GB/T13022	%	180	180
	TD	GB/T13022	%	65	65
Shrinkage (250°F / 2min)	MD	Q/SN2	%	2.0	2.0
	TD	Q/SN2	%	1.0	1.0
Seal Strength (260°F/0.75sec/20psi)	PVdC-PVdC	Q/SN2	g/in	550	570
Seal Strength 200g/inch @	PVdC-PVdC	Q/SN2	°F	220	220
BARRIER					
Water Vapor Transmission Rate	100°F/90% RH	ISO 15106-3	g/100in ² /24h	0.27	0.25
Oxygen Transmission Rate	73°F/0% RH	ASTM D3985	cc/100in ² /24h	0.77	0.77

Guidelines for storage

Temperature should be less than 86°F and humidity 55±5% in storage areas. Material should be consumed within 6 months of receipt. Allow film to reach operating room temperature 24h before use.

Printing & Lamination

It is recommended to print on the Acrylic coated side of this film. Advice should be taken from your ink supplier.

FDA Compliance: For information regarding food contact compliance, please contact your Impak Films representative

Information in this publication refers to average values of reference data and/or laboratory tests on samples from standard production. It is believed to be accurate and is given in good faith, but it is for the customer to determine the suitability of the material for its own particular purpose or application. Accordingly, Impak Films USA LLC gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. This document is not a product specification. Impak Films reserves the right to amend this product data sheet at any time without prior notification.

IMPAK FILMS AUSTRALIA (www.impakfilms.com.au)
ABN: 42 586 823 597 Address: Unit 1, 15-21 Butler Way, (P.O. Box 1114), Tullamarine Vic. 3043, Australia Telephone: +61 3 9310 5540 Facsimile: +61 3 9310 5590

IMPAK FILMS USA (www.impakfilms.com)
Address: 2300 Lake Park Drive, Suite 270, Smyrna, Georgia 30080, USA Telephone: +1 678 384 5520 Facsimile: +1 678 384 5543