




TECHNICAL DATA SHEET

TRANSPARENT, VERY HIGH BARRIER PET FILM

IMP242



AIOx top coated, very high barrier polyester surface
Transparent polyester core

IMP242 is a transparent AIOx PET film which has been top coated to give very high oxygen barrier and improved moisture barrier properties. IMP242 is suitable for printing and lamination and is designed for use in a variety of flexible packaging applications.

PRODUCT FEATURES

- Very high oxygen and moisture barrier
- Excellent gloss and transparency
- Can be printed and laminated on the top coated side
- Suitable for use in microwave applications
- Suitable for use in metal detector inspection processes

APPLICATIONS

- Very high barrier products that are not light sensitive
- Suitable for meat, fish, nuts, dried fruit, cheese and dried meats
- Used in a laminate structure to provide very high barrier flexible material suitable for form fill and seal, pouch, bag and lidding applications.

PROPERTIES	TEST METHOD		UNITS	IMP242	IMP242	IMP242
GENERAL						
Thickness		Internal	ga	41	49	92
		Internal	lb/ream	8.85	10.63	20.0
Yield		Internal	in ² /lb	48800	40600	21600
Surface Tension	Coated	ASTM D-2578	dynes/cm	43	43	43
OPTICAL						
Haze	max	ASTM D-1003	%	2.0	2.0	2.2
MECHANICAL						
Tensile Strength	MD	ASTM D-882	psi	28800	28800	28800
	TD	ASTM D-882	psi	28800	28800	28800
Elongation to Break	MD	ASTM D-882	%	200	200	200
	TD	ASTM D-882	%	200	200	200
Shrinkage 300°F / 30 min	MD	ASTM D-1204	%	2.0	2.0	2.0
	TD	ASTM D1204	%	0.5	0.5	0.5
Coefficient of Friction	Uncoated side	ASTM D-1894		<0.55	0.55	<0.55
BARRIER						
Water Vapor Transmission Rate	(100°F/90% RH)	ASTM E96	g/100in ² /24h	0.07	0.07	0.06
Oxygen Transmission Rate	(73°F/0% RH)	ASTM D3985	cc/100in ² /24h	0.03	0.03	0.03

Guidelines for storage

IMP242 should be stored at below 105°F in its original wrapping and away from sources of direct sunlight.

Printing & Lamination

Consult with your ink and adhesive suppliers for appropriate materials for use with this product.

FDA Compliance: For information regarding food contact compliance, please contact your Impak Films representative

Information in this publication refers to average values of laboratory tests on samples from standard production. It is believed to be accurate and is given in good faith, but it is for the customer to satisfy the suitability for its own particular purpose. Accordingly, Impak Films gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. This document is not a product specification. Impak Films reserves the right to change the data sheet at any time without prior notification.

IMPAK FILMS AUSTRALIA (www.impakfilms.com.au)

ABN: 42 586 823 597 Address: Unit 1, 15-21 Butler Way, (P.O. Box 1114), Tullamarine Vic. 3043, Australia Telephone: +61 3 9310 5540 Facsimile: +61 3 9310 5590

IMPAK FILMS USA (www.impakfilms.com)

Address: 2300 Lake Park Drive, Suite 270, Smyrna, Georgia 30080, USA Telephone: +1 678 384 5520 Facsimile: +1 678 384 5543