



# IMPAK FILMS US LLC

## Recyclable Films

Product	Description	Gauge	Yield in <sup>2</sup> /lb	Barrier		Key Properties	
				WVTR	OTR	Optical	Other
<b>RECYCLABLE BOPE</b>							
IMP080	Two Side Heat Sealable BOPE Film	100	30,350	-	-	Haze: 4.5% to 6.5% Gloss: ≥ 75	Heat Seal Strength: > 2,500 g/in
		120	25,300	-	-		
		160	18,950	-	-		
		200	15,100	-	-		
IMP082	Non-Heat Sealable Print Web BOPE Film	80	37,800	-	-	Haze: 5.0% to 7.0% Gloss: ≥ 90	COF: ≤ 0.40
		100	30,350	-	-		
		120	25,300	-	-		
IMP083	Non-Heat Sealable Matte BOPE Film	100	30,350	-	-	Haze: ≥ 70%	COF: Gloss side: ≤ 0.40 Matte side: ≤ 0.50
		120	25,300	-	-		
		160	18,950	-	-		
		200	15,100	-	-		
<b>RECYCLABLE PCR PET</b>							
IMP295	Corona Treated PET with 90% PCR	48	41,850	2.70	6.60	Haze: 2.5%	COF: Static: 0.55 Dynamic: 0.50
IMP296	AlOx Top Coated PET with 70% PCR	50	40,300	0.04	0.04	Haze: 2.5%	COF: Static: 0.55 Dynamic: 0.50
IMP297	Matte PET with 70%PCR	48	41,850	2.90	9.70	Haze: 45%	COF: Static: 0.44 Dynamic: 0.38
		90	21,800	1.90	5.15		